



END USE RETENTION COMPARISON

END USE	PRESERVATIVES			
	MICRONIZED COPPER AZOLE	MICRONIZED COPPER QUATERNARY	ALKALINE COPPER QUATERNARY	CHROMATED COPPER ARSENATE
Above Ground - Fencing	0.05	0.15	0.15	n/a
Above Ground - General Use	0.06	0.15	0.25	n/a
Ground Contact - General Use	0.15	0.34	0.40	n/a
Ground Contact - Critical Structural	0.23	0.60	0.60	0.60